



## FLEXCOMP® ME-A

### Kundeninformation / Customer information

#### Kurzbeschreibung.

Die Serie FLEXCOMP® ME-A ist eine platinkatalysierte (additionsvernetzende) Hochleistungs-Siliconmischung mit erhöhter elektrischer Leitfähigkeit.

#### Typische Eigenschaften.

Temperaturbereich -50 bis +200°C.  
Zu verarbeiten in Spritzguss und Extrusion.

#### Weitere Informationen.

Zu weiteren individuellen Informationen und Daten, wie z.B. der Topfzeit Ihres Compounds, mögliche Härteabstufungen oder weiterer Konformitäten/Zertifikate fragen Sie bitte unseren technischen Service.

#### Short description.

The series FLEXCOMP® ME-A is a platinum catalyzed (addition cured) high performance silicone compound with increased electrical conductivity.

#### Typical properties.

Temperature range -50 to +200°C.  
For transformation by moulding and extrusion.

#### Further informations.

Please contact our technical service for further information and data on your individual compound, such as pot life, further possible alternations of hardness or further compliances/certifications.

### Ausgewählte Beispiele und typische Werte der Serie FLEXCOMP® ME-A<sup>1</sup> / Exclusive examples and typical values of the series FLEXCOMP® ME-A<sup>1</sup>

FLEXCOMP®	Werkstoff <sup>2</sup>	Dichte <sup>3</sup>	Härte <sup>4</sup>	Reißfestigkeit <sup>5</sup>	Reißdehnung <sup>6</sup>	WRW <sup>7</sup>
ME-A 50010-xx	VMQ	1.12	50 ± 5	≥ 4	≥ 350	≥ 8
ME-A 60010-xx	VMQ	1.14	60 ± 5	≥ 5	≥ 280	≥ 10
ME-A 70010-xx	VMQ	1.16	70 ± 5	≥ 6	≥ 250	≥ 11

Werte ermittelt an Musterplatten 2/6 mm, vulkanisiert (Addition) 8 min 140°C, getempert 4h 200°C / Values measured on sample plates 2/6 mm, cured (addition) 8 min at 140°C, post cured 4h at 200°C

Der Platinkatalysator kann durch Schwermetalle, Schwefel- und Stickstoffverbindungen (Amine) irreversibel geschädigt werden. Lagern, Verarbeiten oder Tempern in Kontakt mit diesen Verbindungen (enthalten z.B. in organischem Kautschuk) muss daher ausgeschlossen werden. / The platinum catalyst can be inhibited irreversibly by heavy metals, sulfur or nitrogen (amine) compounds. Storage, transforming or post curing with contact to such substances (as they are e.g. contained in organic rubbers) has to be avoided in any case.

<sup>1</sup> Einsatztemp.bereich / Operating temp. range: -50 — 200 °C, <sup>2</sup> Material: ASTM D 1418, <sup>3</sup> Density: DIN EN ISO 1183-1 A (g/cm<sup>3</sup>), <sup>4</sup> Hardness: DIN 53505 (Shore<sup>®</sup> A), <sup>5</sup> Tensile strength: DIN 53504 – S2 (MPa), <sup>6</sup> Elongation at break: DIN 53504 – S2 (%), <sup>7</sup> Weiterreißwiderstand / Tear resistance: ASTM D 624 B (N/mm)

### **Haftungsausschluss.**

Mitgeteilte Werte sind an Musterplatten ermittelte Richtwerte und nicht zur Erstellung von Spezifikationen bestimmt. Des Weiteren entsprechen die angegebenen Werte und Informationen unserem jeweiligen Wissensstand, stellen den Endbenutzer jedoch nicht von eigenen sorgfältigen Prüfungen frei, ebenso wenig von der Verpflichtung zur Überprüfung eventueller Verletzungen von Schutzrechten Dritter. Änderungen an Benennungen, Werten und Verfahren vorbehalten. Es gelten die Allgemeinen Geschäftsbedingungen der M+S Silicon GmbH & Co. KG, Dortmund.

### **Disclaimer.**

*Values provided in this data sheet have been measured on sample plates and are for information purpose, but not intended to draw specifications. Furthermore, all values and information are in accordance with the present state of our knowledge, but do absolve the user from neither own careful tests nor from the obligation to investigate possible infringement of third parties' rights. We reserve the right to alter assignments, values and processes. Terms and conditions of M+S Silicon GmbH & Co. KG, Dortmund, Germany, are applied.*



### **FLEXCOMP® ist ein Produkt der**

M+S Silicon GmbH & Co. KG  
Hannöversche Strasse 28, 44143 Dortmund, Germany  
Tel. +49(0)231/967890-0 • Fax: +49(0)231/967890-20  
Geschäftsführer: Jürgen Siedler, Jens Gonschorek  
info@ms-silicon.de • www.ms-silicon.de

info@flexcomp.eu • www.flexcomp.eu

M+S Verwaltungs GmbH

Amtsgericht Dortmund • 14840 HRB • 14075 HRA

Zertifiziert nach DIN EN ISO 9001 und DIN EN ISO 14001

©2015 M+S Silicon GmbH & Co. KG FC-CI Version 1.0/06/2015/TB

